

# Technical Information

DESCRIPTION	ASTM	RESULT
Water absorption	C-373	16.0% - Meets or Exceeds
Breaking strength	C-648	189 lbs. - Meets or Exceeds
Resistance to staining	C-1378	Meets or Exceeds
Chemical resistance	C-650	Meets or Exceeds
Resistance to freeze-thaw cycle	C-1026-13	Meets or Exceeds
Bond strength	C-482-02	1.3MPa - Meets or Exceeds
Facial dimensions	C-499-09	Meets or Exceeds
Wedging (rectangularity)	C-502-09	Meets or Exceeds
Wedging (straightness)	C-502-09	Meets or Exceeds
Thickness	C-499-09	Meets or Exceeds
Warpage	C-485-09	Meets or Exceeds
Thermal shock resistance	C-484-99	Meets or Exceeds
Crazing resistance	C-424-93	Meets or Exceeds